



PRODUCT DATA SHEET

KOSKOTE 2100 HY-SERIES

KOSKOTE 2000 HY-SERIES (Epoxy / Polyester Based Powder Coating)

DESCRIPTION

KOSKOTE 2000 HY-Series polyester-epoxy powder coating is based on specially selected resins to give a hard durable finish suitable for a wide range of indoor applications such as domestic appliances and office equipment.

PHYSICAL PROPERTIES

Appearance	: Free flowing fine powder
Colour	: Wide colour range.
Specific gravity	: 1.30 ~1.80 g/cm ³ depend on colour.
Volume Solid	: 100%

SURFACE PREPARATION

Ensure that the surface is properly cleaned and free from oil, grease and other contaminants, Subsequent surface treatments might include blasting, if required, and iron phosphate or zinc phosphate depending on the long term corrosion performance desired.

APPLICATION INSTRUCTION

It is suitable for application by proprietary manual or automatic corona charging guns. Make sure the spray equipment hoses, gun parts and hoppers are clean and free from defuse powder all the contact points should be maintained to ensure metal-to-metal ground. Voltage should be kept between 20~100kV. Spray booth and collection system should maintain to ensure sufficient air velocities.



PRODUCT DATA SHEET

KOSKOTE 2100 HY-SERIES

CURING SCHEDULE

Standard baking temperature : 10 minutes at 180°C (Metal temperature).

COATING THICKNESS

Recommended Thickness : 60~80µm

STORAGE & SHELF LIFE

It is recommended to store below 25°C in dry conditions. When stored under such conditions the shelf life is not exceeding 9 months from the date of manufacture.

PHYSICAL COATING PERFORMANCE

Gloss (ASTM D523 60°) : > 85 %
Direct impact (ASTM D2794) : Greater than 65 kg.cm
Reverse impact (ASTM D2794) : Greater than 65 kg.cm
Adhesion (DIN 53151, 2mm) : Gt = 0
Conical mandrel bend (ASTM D522) : Less than 5 mm
Erichsen Cuppling (DIN 53156) : Greater than 8 mm
Pencil Hardness (ASTM D3363) : H

SALT SPRAY RESISTANCE

According to ASTM B117-73 on-
Zinc phosphated steel : 5 mm undercutting after 1000 hours exposure.
Chromated aluminium : No change after 1000 hours.



PRODUCT DATA SHEET

KOSKOTE 2100 HY-SERIES

HUMIDITY RESISTANCE

According to DIN 50017 : No breakdown after 1000 hours.

SOLVENTS & CHEMICALS RESISTANCE

Good resistance to common acids, alkalis and solvents at room temperature. It may be attacked by nitric acid, ketones and trichloroethylene. Refer to the information sheet " Chemical Resistance of Powder ".

HEALTHY & SAFETY

Avoid skin and eyes contact by wearing suitable overalls, gloves, goggles, etc. Spillage on the skin should immediately be removed by thorough washing with water and soap. Eyes should be well flushed with water and medical attention sought immediately.

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factor affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product data without notice.