



PRODUCT DATA SHEET

KOSSAN 2K PU AUTO REFINISH KAR-21MS CLEAR

DESCRIPTION

KAR-21MS CLEAR is a 2K PU Auto refinish medium solids high gloss clear finish. It provides high gloss, excellent leveling and UV protection :

- ❑ High Gloss and good leveling properties.
- ❑ Excellent UV Protection.
- ❑ Easy Sanding and polishing properties.
- ❑ Very good flow properties and good coverage.
- ❑ Lead-free and Mercury free

PHYSICAL PROPERTIES

Colour	: Clear.
Specific Gravity	: 1.01±0.02 gm/cm ³ .
Solid Content	: 50 % by volume.
Flash Point	:
Mixing Ratio (A/B)	: 2/1 by Volume.
Touch Dry	: minutes
Recoating Time	: Min. 1½ - 2 hours ,Max. unlimited

SURFACE PREPARATION

It is essential to have a properly prepare surface to ensure precise and long lasting coating performance. Surface must be dry, clean, free from any loose material, dirt, grease and other contaminants.

MIXING / APPLICATION

- ❑ Stir paint thoroughly.
- ❑ Mixer KAR-21MS(A) to KAR-21MS(B) with the ratio of 2 to 1 by volume, add suitable amount of Kossan ART-01 thinner then mixed thoroughly prior to spray application.
- ❑ The recoating period is minimum 1½- 2 hours.
- ❑ Cleaner/Thinner : Kossan ART-01.

KOSSAN PAINT (M) SDN.BHD

1 Jalan Koporat 1/KU 9, Taman Perindustrian Meru, 42200 Kapar, Selangor D.E Malaysia
Tel.603 33922799 ; Fax. 603 33923799 ; e-mail lsk@kossanpaint.com.my ; Web-site : www.kossanpaint.com

PRODUCT DATA SHEET

COVERAGE & PACKING SIZE

Coverage : Approx. 8-10 m²/liter/coat
Packing Size : 1.50Ltr-set
(KAR-21MS(A) = 1 Ltr & KAR-21MS(B) = 0.50Ltr).

STORAGE

KAR-21MS Clear has a minimum self-life of 12 months at cool and dry place. Containers must be kept tightly closed in a secure upright position.

HEALTHY & SAFETY

Avoid skin and eyes contact by wearing suitable overalls, gloves, goggles, etc. Spillage on the skin should immediately be removed by thorough washing with water and soap. Eyes should be well flushed with water and medical attention sought immediately.

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factor affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product data without notice.

KOSSAN PAINT (M) SDN.BHD

1 Jalan Koporat 1/KU 9, Taman Perindustrian Meru, 42200 Kapar, Selangor D.E Malaysia
Tel.603 33922799 ; Fax. 603 33923799 ; e-mail lsk@kossanpaint.com.my ; Web-site : www.kossanpaint.com