



PRODUCT DATA SHEET

KOSSAN 2K AUTO REFINISH PRIMER KAR-1000P

DESCRIPTION

KAR-1000P is a fast curing 2K PU Auto refinish primer which pigmented with non-toxic anticorrosive pigments it provides excellent adhesion, leveling properties and easy sand ability properties:

- Fast curing.
- Excellent corrosion properties
- Excellent flow and leveling properties..
- Easy sanding.
- Good hinding power and coverage.
- Lead-free and Mercury free

PHYSICAL PROPERTIES

| | |
|--------------------|---------------------------------------|
| Colour | : Grey. |
| Specific Gravity | : 1.38±0.02 gm/cm ³ . |
| Solid Content | : 50 % by volume. |
| Flash Point | : >26°C |
| Mixing Ratio (A/B) | : 3.95/1 by volume (85/15 by weight). |
| Touch Dry | : 20-30minutes |
| Sanding Time | : Min. 45-60minutes |

SURFACE PREPARATION

It is essential to have a properly prepare surface to ensure precise and long lasting coating performance. Surface must be dry, clean, free from any loose material, dirt, grease and other contaminants.

MIXING / APPLICATION

- Stir paint thoroughly.
- Mixer KAR-1000P(A) to KAR-1000P(B) with the recommended ratio, add suitable amount of Kossan ATR-01 thinner then mixed thoroughly prior to spray application.
- The recoating period is minimum 2-3 hours.
- Cleaner/Thinner : Kossan ART-01.

KOSSAN PAINT (M) SDN.BHD

1 Jalan Koporat 1/KU 9, Taman Perindustrian Meru, 42200 Kapar, Selangor D.E Malaysia
Tel.603 33922799 ; Fax. 603 33923799 ; e-mail lsk@kossanpaint.com.my ; Web-site : www.kossanpaint.com

PRODUCT DATA SHEET

COVERAGE & PACKING SIZE

Coverage : Approx. 8-10 m²/liter/coat
Packing Size : 1.20Ltr-set & 5.0Ltr-set
(KAR-1000P(A) = Ltr & KAR-1000P(B) = Ltr).

STORAGE

KAR-1000P has a minimum self-life of 12 months at cool and dry place. Containers must be kept tightly closed in a secure upright position.

HEALTHY & SAFETY

Avoid skin and eyes contact by wearing suitable overalls, gloves, goggles, etc. Spillage on the skin should immediately be removed by thorough washing with water and soap. Eyes should be well flushed with water and medical attention sought immediately.

DISCLAIMER

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factor affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product data without notice.

KOSSAN PAINT (M) SDN.BHD

1 Jalan Koporat 1/KU 9, Taman Perindustrian Meru, 42200 Kapar, Selangor D.E Malaysia
Tel.603 33922799 ; Fax. 603 33923799 ; e-mail lsk@kossanpaint.com.my ; Web-site : www.kossanpaint.com