



## PRODUCT DATA SHEET

# KOSSAN GALVA WASH KGW-01

(WATER BASED GALVANIZED ZINC TREATMENT SOLUTION)

### DESCRIPTION

Is a water based low VOC blue treatment solution specially formulated for pre-treatment on galvanized zinc / electroplated zinc surfaces to provide subsequent adhesion of a wide range of coatings.

### PHYSICAL PROPERTIES

Colour	: Clear Blue
Specific gravity	: $1.00 \pm 0.02$ gm/cm <sup>3</sup>
Volume Solid	: Nil
VOC	: 182g/liter
Boiling Point	: 100°C
Flash point	: Nil

### SURFACE PREPARATION

Make sure all surface to be treated must first be free from oil, greases, and wax. if this is happen degreasing with solvent and washing down with liquid detergent and rinse well with fresh water and allow to dry.

### MIXING / APPLICATION DATA

Apply Kossan Galva-Wash KGW-01 by brush, roller or dipping. Ensuring that the entire surface change to black colour, then wash down with fresh water and allow to dry thoroughly prior to painting.

Cleaner : Fresh water

### KOSSAN PAINT (M) SDN.BHD

1 Jalan Koporat 1/KU 9, Taman Perindustrian Meru, 42200 Kapar, Selangor D.E Malaysia  
Tel.603 33922799; Fax. 603 33923799; e-mail [isk@kossanpaint.com.my](mailto:isk@kossanpaint.com.my) ; Web-site : [www.kossanpaint.com](http://www.kossanpaint.com)

**THEORITICAL COVERAGE & PACKING SIZE**

Coverage : 10-12.0m<sup>2</sup>/liter.  
Packing Size : 1 Liter; 5 liter & 20Liter Jerrycan.

**STORAGE**

KOSSAN GALVA WASH KGW-01 has a minimum self-life of 12 months at cool and dry place. Containers must be kept tightly closed.

**HEALTY & SAFETY**

Avoid skin and eyes contact by wearing suitable overalls, gloves, goggles, etc. Spillage on the skin should immediately be removed by thorough washing with water and soap. Eyes should be well flushed with water and medical attention sought immediately.

**DISCLAIMER**

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factor affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product data without notice.

**KOSSAN PAINT (M) SDN.BHD**

1 Jalan Koporat 1/KU 9, Taman Perindustrian Meru, 42200 Kapar, Selangor D.E Malaysia  
Tel.603 33922799; Fax. 603 33923799; e-mail [lsk@kossanpaint.com.my](mailto:lsk@kossanpaint.com.my) ; Web-site : [www.kossanpaint.com](http://www.kossanpaint.com)