



# Product Data Sheet

Transocean

## Cleanship Antifouling 2.95

### Product description.

A tinfree polishing antifouling based on specially developed mixture of polymers and pigmented with a combination of biocides. The surface is self-abrasive by a careful adjusted balance of hydrophobic and hydrophilic binders. This mechanism enables leaching control and allows easy recoating after service life. The product is suitable for vessels trading in coastal and tropical waters.

### Physical properties.

Colour/Texture	Redbrow, Pink, Blue, Black/Mat
Volume Solids	52%
Specific gravity	1.75 gr/ml
VOC	425 gr/liter
Flashpoint	>25°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m <sup>2</sup> /l)
Range	75 – 150	150 – 295	6.8 – 3.8
Recommended	125	245	4.1

### Application data.

Guiding data Airless spray Pressure at nozzle: 120 -180 bar. Nozzle size: 0.41 - 0.58 mm.  
Spray angle: 40 - 80 degrees.  
Volume of thinner: 0 - 3%.

Brush/Roller Suitable but airless spray is preferred. Multicoats may be needed to achieve the specified dry film thickness.  
Volume of thinner: 0 - 5%.

Thinner/Cleaner Transocean Special Thinner 6.01.  
Avoid excessive thinning as it will result in lower sag resistance and slower cure.

### Drying and recoating times (1).

Substrate temperature	Touch dry	Hard dry	Dry to recoat		Minimum drying time for undocking
			Minimum	Maximum (1)	
10 °C	1 hour	8 hours	8 hours	6 months	16 hours
23 °C	1 hour	6 hours	6 hours	6 months	12 hours
30 °C	30 minutes	4 hours	4 hours	3 months	12 hours

- (1) The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, preceding paint system etc
- (2) The surface should be dry and free from fouling and other contaminants prior to overcoating. When in doubt, consult your nearest Transocean office.

### Surface preparation.

Coated substrates The surface must be dry and free from fouling, salts and other contaminants. Remove salts and dirt by fresh water washing and hard fouling by scraping. Corroded and/or damaged areas should be repaired first with an appropriate primer system.

## Recommended paint system.

Transocean Cleanship Antifouling 2.95 can be applied on Transpoxy and Transvinyl priming systems. A typical system is shown below.

Transpoxy Masterbond BT 4.68	1-2 x 150 $\mu$ dft each.
Transvinypox 2.06	1 x 75 $\mu$ dft.
Transocean Cleanship Antifouling 2.95	2 x 150 $\mu$ dft (up to 60 months protection).

Life times expectations are difficult to give, as it is dependent on many factors beyond our control such as vessel's speed and sailing pattern, seawater quality and temperature. Therefore the above stated antifouling specification should be used for guidance only. Consult your Transocean representative for more information.

## Application conditions.

The temperature of the substrate should be at least 3°C above the dew point of the air. Temperature and relative humidity should be measured in the vicinity of the substrate.

The maximum recommended surface temperature is approx. 40°C. Higher steel temperatures are acceptable provided dry-spray is avoided by proper spray application and extra thinning if required. In extreme cases it may be necessary to reduce film thickness in order to avoid sagging.

When applying the paint in confined spaces, provide adequate ventilation during application and drying.

The temperature of the mixed paint should be at least 15°C, otherwise extra solvent may be required to obtain a proper application viscosity.

## Storage and shelf life.

The product must be stored in accordance with national regulations. The cans are to be kept in a dry, cool, well ventilated space and away from source of heat and ignition. Cans must be kept tightly closed.

## Worldwide availability

The product is part of the common Transocean product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and/or national regulations. In such cases an alternative datasheet will be issued.

## Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spraying should be carried out under well-ventilated conditions. This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

## Disclaimer

*The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.*

Date of issue: August, 24.



KOSSAN PAINT (M) SDN.BHD  
1, Jalan Koporat 1/KU9, Taman Perindustrian Meru,  
Kapar, 42200 Klang Selangor D.E Malaysia.  
Tel. 6033922799 ; Fax.6033923799 ; e-mail : sales@kossanpaint.com.my  
web-site : www.kossanpaint.com